

## TYPE

A self-crosslinking acrylic dispersion, belonging to our ECOWISE CHOICE product range for selected applications (contact your allnex representative for more information).

SETAQUA 6726 offers higher hardness, quicker stackable and better sandability than SETAQUA 6716, and leads to paints with better viscosity stability.

## FORM OF DELIVERY (F.O.D)

40.0 % non-volatile in demineralized water

## PRODUCT DATA

<b>Solids content, by wt:</b>	40.0 - 42.0 %
<b>Viscosity, Brookfield (23°C):</b>	Max. 0.72 Pa.s
<b>pH (25°C):</b>	7.6 – 8.6
<b>Appearance:</b>	Light white emulsion

### Not continually determined:

<b>MFFT:</b>	30 - 35 °C
<b>Density (20°C):</b>	1.04 kg/dm <sup>3</sup>

## PERFORMANCE HIGHLIGHTS

SETAQUA 6726 is ideally suited as a highly transparent, colourless clear coat and pigmented coat, especially for the applications where quick anti-blocking, sandability and adhesion are requested, but no significant increased use of co-solvents. Good filling property is provided by white paints based SETAQUA 6726, like on MDF.

## PRECAUTIONS

Before using SETAQUA 6726, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

## STORAGE AND HANDLING

Storage should be under cover, out of direct sunlight and avoiding extreme temperature changes. Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

Storage temperature: 5 - 35 °C.

## SHELF LIFE

Standard shelf life is 365 days from the date of manufacturing. For products still in allnex possession allnex may extend the expiration date of a batch upon re-testing by QC.