

A surfactant free aqueous dispersion of acrylic polymers.

SOLVENT COMPOSITION

Demineralized water

SPECIFICATIONS

Non-Volatiles: 39 - 41 %

ISO 3251, *STM 001G*

pH: 6.0 - 8.0

STM 007A

TYPICAL PROPERTIES

MFFT: approx. 64 °C

ASTM D 2354, *STM 087A*

Density: approx. 1.04 kg/dm³

DIN 53217

TECHNICAL FEATURES

Fast drying, high film hardness, good blocking resistance and good sandability.

APPLICATION

Air-drying or forced drying interior and exterior pigmented and non-pigmented wood finishes for the furniture industry.

STORAGE CONDITIONS

SETAQUA 6406 should not be stored at temperatures below 0 °C or above 35 °C. Avoid exposure to direct sunshine and prevent freezing.

SHELF LIFE

Standard shelf life is 365 days from the date of manufacturing, but may be extended based upon retesting by allnex Quality Control.

REMARKS

STM: allnex method of determination (available on request).

STM 001G: spreading agent is demineralized water.

Use a paper clip to spread out.

The determination of flash point is not applicable.