

### General Description

CRYLCOAT® 2476-2 is a medium reactive carboxyl functional polyester resin designed for curing with TGIC in the ratio of 94/6 for architectural applications. Coatings based on CRYLCOAT® 2476-2 exhibit good outdoor durability, gloss, flow out and excellent storage stability of powder coatings formulations.

(Formerly CRYLCOAT E 04776)

Preliminary Technical Data Sheet

### Saturated Polyester Resin

#### Product Specification

	Limits
Appearance	Pale granules
Brookfield Viscosity @ 200 °C, mPa.s	Approx. 7300
Color, b-value	Max. 15
Acid value (mg KOH/g)	Approx. 29

#### Shelf Life

Under normal storage conditions ( $\leq 30^{\circ}\text{C}$ ), the shelf life of the resin will be 24 months from date of manufacturing. For product older than 24 months, it is recommended to check the acid value and the viscosity every year.

#### Safety & Environmental Protection

For more information, please refer to the Material Safety Data Sheet.

March 2021 – Supersedes previous versions

#### Other Properties

	Typical value
Glass transition ( $^{\circ}\text{C}$ )	Approx. 67