

A surfactant free aqueous dispersion of acrylic polymers.

SOLVENT COMPOSITION

Demineralized water

SPECIFICATIONS

Non-Volatiles: 39 - 41 %

ISO 3251, *STM 001G*

Viscosity Brookfield: Max. 100 cPa.s

ISO 2555, *STM 012F*

pH: 7.5 - 9.5

STM 007A

TYPICAL PROPERTIES

MFFT: approx. 18 °C

ASTM D 2354, *STM 087A*

Density: approx. 1.03 kg/dm³

DIN 53217

TECHNICAL FEATURES

SETAQUA 6768 contains dual self crosslinking mechanisms for improved adhesion, hardness, chemical resistance, blocking, fast drying and outdoor durability.

APPLICATION

Air-drying interior and exterior pigmented and non pigmented wood finishes for the joinery industry.

STORAGE CONDITIONS

SETAQUA 6768 should not be stored at temperatures below 0 °C or above 35 °C. Avoid exposure to direct sunshine and prevent freezing.

SHELF LIFE

Standard shelf life is 365 days from the date of manufacturing, but may be extended based upon retesting by allnex Quality Control.

REMARKS

STM: allnex method of determination (available on request).

STM 001G: spreading agent is demineralized water.

Use a paper clip to spread out.

STM 012F: Brookfield RVT, 23 °C, spindle 2, 50 rpm.

The determination of flash point is not applicable.