

An air drying long oil alkyd resin based on soya bean oil.

SOLVENT COMPOSITION

D40 solvent / xylene (87.5 / 12.5)

SPECIFICATIONS

Non-Volatiles: ISO 3251, <i>STM 001G</i>	59 - 61 %
Viscosity (23 °C at 100 s⁻¹): ISO 3219, <i>STM 012J</i>	3.5 - 7.0 Pa.s
Acid value (as such): ISO 3682, <i>STM 303A</i>	4.1 - 6.9 mg KOH/g
Colour GARDNER (Lico): ISO 4630, <i>STM 008E</i>	Max. 6.0 Gardner
Appearance: <i>STM 017A</i>	clear and clean

TYPICAL PROPERTIES

Density: DIN 53217	approx. 1.00 kg/dm ³
Flash point: ISO 1523	approx. 38 °C

REMARKS

STM: allnex method of determination (available on request).

STM 001G: spreading agent is xylene.

TECHNICAL FEATURES

Fast drying, excellent hardness, very good water resistance and durability.

APPLICATION

- Marine and Protective coatings
- Architectural paints: primers, stoppers, undercoats and finishes on wood and metal, for interior and exterior use
- Do-it-yourself paints.

STORAGE CONDITIONS

Keep container tightly closed and dry in a cool, well-ventilated place. Keep away from heat, sparks, flame and other sources of ignition.

SHELF LIFE

Standard shelf life is 545 days from the date of manufacturing, but may be extended based upon retesting by allnex Quality Control.