

**TYPE**

Amine blocked acidic catalyst

**FORM OF DELIVERY**

ACTIVE SUBSTANCE (PTSA)  
APPROX. 25 %E

**Determined per batch:**

**Dynamic Viscosity DIN EN ISO 3219**

dynamic viscosity (100 1/s; 23 °C)	[mPa.s]	< 10
---------------------------------------	---------	------

**Non-Volatile Matter DIN EN ISO 3251**

non-volatile matter (1 h; 120 °C; 2 g)	[%]	34 - 36
---	-----	---------

**Not continually determined:**

**Colour / Appearance VLN 250**

appearance		clear
colour		colourless to slightly yellow

**Density (Liquids) DIN EN ISO 2811-2**

density approx. (20 °C)	[g/cm <sup>3</sup> ]	0,95
-------------------------------	----------------------	------

**Flash Point DIN EN ISO 1523**

flash point approx.	[°C]	9
------------------------	------	---

**SPECIAL PROPERTIES AND USE**

CYCAT® VXK 6395 was developed for cross-linking reaction of urea and melamine curing systems at low temperatures. Typical application areas are stoving paint systems for general industry and for OEM automotive systems.

**PROCESSING**

The added quantity depends on the application and basic resin and varies between 0.4 – 0.8 %, calculated on total resin content.

**STORAGE**

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 365 days.