

A surfactant free aqueous dispersion of acrylic polymers, belonging to our ECOWISE™ CHOICE product range for Industrial Wood.

SOLVENT COMPOSITION

Demineralized water

SPECIFICATION

Non-Volatiles: 39 - 41 %

ISO 3251, STM 001G

pH: 6.0 - 7.0

STM 007A

TYPICAL PROPERTIES

MFFT: approx. 17 °C

ASTM D 2354, STM 087A

Density: 1.05 kg/dm³

DIN 53217

TECHNICAL FEATURES

Impregnating stains formulated with SETAQUA 6405 exhibit excellent flow and uniform staining properties when used in dip processes.

SETAQUA 6405 can be formulated into tannin stain blocking primers with very good sandability.

APPLICATION

Impregnating stains and tannin blocking primers for hard wood

STORAGE CONDITIONS

This product should not be stored at temperatures below 5°C or above 35°C. Avoid exposure to direct sunlight and prevent from freezing.

REMARKS

STM: allnex method of determination (available on request).

STM001G: spreading agent, demineralized water. Use a paper clip to spread out.

The determination of flash point is not applicable.

While formulating with SETAQUA 6405, care must be taken to keep the pH value below 7.5 .