

An acrylic polyol with 3.6 % OH (calculated on non-volatiles).

SOLVENT COMPOSITION

Xylene

SPECIFICATIONS

Non-Volatiles:	59 - 61 %
ISO 3251, <i>STM 001G</i>	
Viscosity (23 °C at 100 s⁻¹):	(at 59%) 0.14 - 0.50 Pa.s
ISO 3219, <i>STM 012J</i>	
Viscosity (23 °C at 100 s⁻¹):	(at 60%) 0.16 - 0.56 Pa.s
ISO 3219, <i>STM 012J</i>	
Viscosity (23 °C at 100 s⁻¹):	(at 61%) 0.18 - 0.62 Pa.s
ISO 3219, <i>STM 012J</i>	
Acid value (as such):	2.3 - 4.9 mg KOH/g
ISO 3682, <i>STM 303A</i>	
Colour APHA (Lico):	Max. 50 APHA
ISO 6271, <i>STM 008F</i>	
Appearance:	clear and clean
<i>STM 017A</i>	

TYPICAL PROPERTIES

Density:	1.01 kg/dm ³
DIN 53217	
Flash point:	27 °C
ISO 1523	

REMARKS

STM: allnex method of determination (available on request).

STM 001G: spreading agent is xylene.

TECHNICAL FEATURES

In combination with aliphatic polyisocyanates: excellent mechanical properties and chemical resistance, high-medium solids.

In combination with Vestanat T 1890 S: high solid, high build, good gloss, excellent outdoor durability and light fastness, good mechanical properties.

APPLICATION

- Industrial two-component coatings with excellent flexibility and mechanical properties (in combination with polyisocyanates such as Desmodur N).
- Mixing resin for two-component systems to optimize/improve the flexibility.
- Combination with Vestanat 1890 S

STORAGE CONDITIONS

Keep container tightly closed and dry in a cool, well-ventilated place. Keep away from heat, sparks, flame and other sources of ignition.

SHELF LIFE

Standard shelf life is 720 days from the date of manufacturing, but may be extended based upon retesting by allnex Quality Control.

COMPATIBILITY

% SETALUX 1187 XX-60	90	75	50	25	10
% of other material	10	25	50	75	90
<i>Acrylic polyols</i>					
SETALUX 1151 XX-51	+	+	+	+	+
SETALUX 1152 XX-51	+	+	+	+	+
SETALUX 1186 SS-60	+	+	+	+	+
<i>Short oil alkyd</i>					
SETAL 84 XX-70	+	+	+	+	+
<i>Other materials</i>					
Desmodur N 75	+	+	+		
Desmodur L 75	+	+	+		
Desmodur N 3390	+	+	+		
Desmodur HL	-	-	-		
Desmodur IL	+	+	-		
Vestanat B1370	+	+	+		
CAB 551-0.01	+	+	+		
Ucar vinyl resin VAGH	+	+	+		
Ucar vinyl resin VROH	+	+	+		
Nitrocellulose 1/2 s	+	+	+		

Suitable mixing proportions (calculated on non-volatiles) are marked '+'.
Combinations in the proportions marked '-' are not recommended.

Suppliers

Desmodur	Covestro
Vestanate	Evonik
CAB	Eastman
Ucar	DowDupont
Nitrocellulose	Hagedorn

DILUTABILITY

Aliphatics	white spirit	not dilutable
Aromatics	xylene	partly dilutable
Esters	ethyl acetate	dilutable
	butyl acetate	dilutable
Ketones	acetone	dilutable
Alcohols	ethanol	dilutable
	butanol	dilutable