

### PRELIMINARY PRODUCT INFORMATION

#### TYPE

Cationic, highly molecular resinlike wetting and dispersing agent for inorganic and organic pigments

#### FORM OF DELIVERY (f.o.d.)

##### Active substance

approx. 30 %

### DEVELOPMENT PRODUCT

This product is serving for trial purposes only. Deviations which might occur during transfer into manufacturing in a commercial scale are possible and do not constitute any material defect.

### TENTATIVE PRODUCT DATA

#### Determined per batch:

##### Colour / Appearance VLN 250

colour		yellow-brown
appearance		clear

##### Non-Volatile Matter DIN 55671

non-volatile matter	[%]	29 - 31
(150 °C; 10 min; 0,5 g)		

##### Iodine Colour Number DIN 6162

iodine colour number		<= 12
----------------------	--	-------

#### Not continually determined:

##### Density (Liquids) DIN EN ISO 2811-2

density	[g/cm <sup>3</sup> ]	1,01
approx.		
(20 °C)		

##### Flash Point DIN EN ISO 1523

flash point	[°C]	44
approx.		

##### Appearance

low viscous liquid

### SPECIAL PROPERTIES

Additol VXL 6237 N improves the wetting of very difficult-to-disperse pigments, specially in aromatic free solventborne highgrade automotive series, car repair and industrial paints.  
Shortens the dispersing time.  
Prevents the reflocculation of the pigments.  
Improves gloss and levelling.

### SUGGESTED USES

Additol VXL 6237 N permits a higher pigmentation of the mill base without increasing viscosity and shortens the dispersing time. The ready pigment pastes and paints are distinguished by a high colloidal stability and do not tend to a reflocculation of the pigments.

By using Additol VXL 6237 N in solvents containing acrylate systems, a stabilizing effect on the binder can be observed.

### PROCESSING

Additol VXL 6237 N must be ground jointly with the pigments. The recommended quantity to be added, calculated on pigment, is as follows for inorganic pigments 3.0 - 10.0 % for organic pigments 10.0 - 50.0 %.

We recommend determining the optimum quantity of Additol VXL 6237 N for each pigment or each pigment blend.

Possible foam formation in the mill base may be prevented by addition of Additol XL 490/50BAC. This additive improves the levelling at the same time.

### STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

Opened vessels have to be closed immediately.

### DISTINGUISHING FEATURES

Additol VXL 6237 N is a non-crystallizing version of Additol VXL 6237, which allows storage at low temperatures with unchanged application characteristics.

In comparison to Additol XL 260 and Additol VXL 6212 Additol VXL 6237 N has a much better effectiveness in aliphatic solvent based resins.

### REMARK:

**Data contained in this publication are based on careful investigations (and are intended for information only). Due to scale up of this product there is not yet sufficient experience concerning serial production. We can therefore not exclude, that based on future knowledge product data and other indicated properties in upcoming Technical Data Sheets will be subject to change. We reserve the right to leave the product name unchanged, even if product data or other indicated properties will vary from the present product info. Regardless of the data contained in this publication any user is obliged to carry out tests under his own responsibility as to the suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products. We apply our General Sales Conditions.**