

A pure long oil alkyd resin based on soya-bean oil.

### SOLVENT COMPOSITION

White spirit

### TYPICAL PROPERTIES

<b>Non-Volatiles:</b>	70 %
ISO 3251, <i>STM 001G</i>	
<b>Viscosity Gardner-Holdt (at 25°C):</b>	Z5 - Z6 GH
ASTM D 1545, <i>STM 012A</i>	
<b>Acid value (on solid resin):</b>	8 mgKOH/g
DIN 53402, <i>STM 041A</i>	
<b>Colour GARDNER (Lico):</b>	6 Gardner
ISO 4630, <i>STM 008E</i>	
<b>Density (at 25°C):</b>	0.96 kg/dm <sup>3</sup>
DIN 53217	

### REMARKS

Recommended Driers  
(As % metal on resin solid)

Cobalt 0.04%  
Zirconium 0.20%  
Calcium 0.10%

### TECHNICAL FEATURES

SETAL® FL70/70 is a pure long oil alkyd resin based on soya-bean oil, which exhibits excellent durability, gloss and gloss retention, through dry and colour retention.

### APPLICATION

SETAL® FL70/70 is recommended for use in undercoats, marine finishes and architectural enamels for interior and exterior use.

### STORAGE

Setal FL70/70 should be stored under cover, out of direct sunlight and avoiding extreme temperature changes. Under normal storage conditions (5 – 35°C, away from extremes) sealed, unopened containers of this material would have a shelf life of 12 months from the date of manufacture. If stored for longer than 12 months, product must be rechecked for suitability in the intended application.

### SAFETY

Refer to Safety Data Sheet before handling or use.