

A pigment dispersing resin.

## SOLVENT COMPOSITION

Demineralized water

## SPECIFICATIONS

**Non-Volatiles:** 49 - 51 %

ISO 3251, STM 001G

**pH:** 7.5 - 8.5

STM 007A

## TYPICAL PROPERTIES

**MFFT:** approx. 52 °C

ASTM D 2354, STM 087A

**Density:** 1.03 kg/dm<sup>3</sup>

DIN 53217

## REMARKS

STM: allnex method of determination (available on request).

STM 001G: spreading agent is demineralized water.

Use a paper clip to spread out.

The determination of flash point is not applicable.

## TECHNICAL FEATURES

SETAQUA 6376 is a very efficient water borne, VOC-free pigment dispersion resin.

Pigment dispersions and pastes based on SETAQUA 6376 impart enhanced properties to water borne coatings manufactured with a variety of binders. Coatings show fast cohesive strength, water resistance development and improved chemical resistance.

SETAQUA 6376 is particularly suitable for coatings that require coffee stain resistance.

## APPLICATION

Water borne, pigmented furniture and kitchen cabinet topcoats.

## STORAGE CONDITIONS

This resin should not be stored at temperatures below 0 °C or above 35 °C. Avoid direct exposure to sunshine and prevent from freezing.

## SHELF LIFE

Standard shelf life is 365 days from the date of manufacturing, but may be extended based upon retesting by allnex Quality Control.