

PRELIMINARY PRODUCT INFORMATION

TYPE

Waterborne, polyether-based polyurethane dispersion, solventfree

FORM OF DELIVERY (f.o.d.)

33 % in water (33WA)

DEVELOPMENT PRODUCT

This product is serving for trial purposes only. Deviations which might occur during transfer into manufacturing in a commercial scale are possible and do not constitute any material defect.

Neutralization agent

approx. 1 % triethylamine, as salt

TENTATIVE PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219

| | | |
|---------------------------------------|---------|---------|
| dynamic viscosity (100 1/s; 23 °C) | [mPa.s] | 5 - 100 |
|---------------------------------------|---------|---------|

Acid Value DIN EN ISO 2114

| | | |
|-------------------------------------|------------|---------|
| acid value (non volatile matter) | [mg KOH/g] | 15 - 23 |
|-------------------------------------|------------|---------|

pH-Value DIN ISO 976

| | | |
|--------------------|--|------------|
| pH-value (10 %) | | 9,1 - 10,6 |
|--------------------|--|------------|

Non-Volatile Matter DIN EN ISO 3251

| | | |
|---|-----|---------|
| non-volatile matter (1 h; 125 °C; 1 g) | [%] | 32 - 34 |
|---|-----|---------|

Not continually determined:

Colour / Appearance VLN 250

| | | |
|------------|--|-----------------|
| colour | | whitish |
| appearance | | slightly cloudy |

Particle Size VLN 220

| | | |
|--------------------------|------|--------|
| particle size (25 °C) | [nm] | <= 150 |
|--------------------------|------|--------|

Density (Liquids) DIN EN ISO 2811-2

| | | |
|-------------------------------|---------|------|
| density approx. (20 °C) | [g/cm³] | 1,02 |
|-------------------------------|---------|------|

Glass Transition Temperature DIN EN 61006

| | | |
|---|------|----|
| glass transition temperature (dynamic mechanical analysis; 10 K/min) | [°C] | 24 |
|---|------|----|

Flash Point (Pensky-Martens) DIN EN ISO 2719

| | | |
|-------------|------|------|
| flash point | [°C] | > 94 |
|-------------|------|------|

SPECIAL PROPERTIES AND USE

Daotan TW 6491 is a waterborne, high molecular weight, polyether- based Polyurethane dispersion, free of solvents and emulsifiers. Coatings based on Daotan TW 6491 provide quick drying and yield transparent, crack free films without further addition of co- solvents. Outstanding features are very high elasticity and elongation.

Compared to Daotan TW 6492 film hardness of Daotan TW 6491 is lower but elasticity is higher.

To further improve water- and chemical resistance properties of coatings dried at ambient temperature Daotan TW 6491 can be crosslinked with
 - Polyaziridine (e. g. Crosslinker CX-100, Fa. DSM, Netherlands)
 - Carbodiimide (e. g. Crosslinker XL-701 or XL-702, Fa. Picassian Polymers, Netherlands)

COMPATIBILITY

Compatibility of Daotan TW 6490 with other resins or additives has to be checked case by case. According to our experience the dispersing additive Additol VXW 6208 and the leveling and substrate wetting agent Additol VXW 6503 lead to excellent results.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 365 days.

It is important to protect Daotan TW 6491/33WA from frost; at low temperatures it has therefore to be stored under frostproof conditions.

Lowest storage temperature: 5 °C

REMARK:

Data contained in this publication are based on careful investigations (and are intended for information only). Due to scale up of this product there is not yet sufficient experience concerning serial production. We can therefore not exclude, that based on future knowledge product data and other indicated properties in upcoming Technical Data Sheets will be subject to change. We reserve the right to leave the product name unchanged, even if product data or other indicated properties will vary from the present product info. Regardless of the data contained in this publication any user is obliged to carry out tests under his own responsibility as to the suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products. We apply our General Sales Conditions.