

TYPE

An air-drying long oil alkyd.

SOLVENT COMPOSITION

D60 solvent

SPECIFICATIONS

Non-Volatiles: ISO 3251, <i>STM 001G</i>	87 - 89 %
Viscosity (23°C at 100 s-1): ISO 3219, <i>STM 012J</i>	7.0 - 11 Pa.s
Acid value (as such): ISO 3682, <i>STM 303A</i>	4.4 - 8.2 mg KOH/g
Colour GARDNER (Lico): ISO 4630, <i>STM 008E</i>	max. 3.0 Gardner
Appearance: <i>STM 017A</i>	clear and clean

TYPICAL PROPERTIES

Density: DIN 53217	approx. 0.97 kg/dm ³
Flash point: ISO 1523	approx. 71 °C

REMARKS

STM: allnex method of determination (available on request).

STM 001G: spreading agent is xylene.

TECHNICAL FEATURES

A high solids alkyd with excellent outdoor durability and very low yellowing in the dark.

Renewable carbon content: 75 - 85 % on solid resin (65 - 75 % on supply form).

APPLICATION

SETAL 312 HD-88 is used in high solids trim paints, decorative topcoats for indoor and outdoor both clear and pigmented

STORAGE CONDITIONS

Keep container tightly closed and dry in a cool, well-ventilated place. Keep away from heat, sparks, flame and other sources of ignition.

SHELF LIFE

Standard shelf life is 545 days from the date of manufacturing.