

A thermosetting hydroxylated acrylic copolymer modified with Sag Control Agent (SCA) light.

### SOLVENT COMPOSITION

Solvent naphtha / n-butanol (98 / 2)

### SPECIFICATIONS

<b>Non-Volatiles:</b> ISO 3251, STM 001G	58 - 62 %
<b>Viscosity flowcurve C&amp;P (1000 s<sup>-1</sup>):</b> STM 012E	1.9 - 4.2 Pa.s
<b>Viscosity flowcurve C&amp;P (1 s<sup>-1</sup>):</b> STM 012E	16 - 26 Pa.s
<b>Amine content:</b> STM 040A	Max. 8.0 mmol /kg
<b>SCA content:</b> STM 032A	3.5 - 4.5 %
<b>Fineness:</b> ISO 1524, STM 024A	Max. 15 microns

### TECHNICAL FEATURES

Excellent appearance due to an optimal balance between flow and sagging, excellent carwash, acid and solvent resistance, excellent gloss, good mechanical properties.

### APPLICATION

Clearcoats for wet-on-wet metallic systems for the automotive industry.

### STORAGE CONDITIONS

SETALUX 71761 VB-60 should be stored and transported in its original sealed containers at temperatures below 40 °C. Avoid exposure to direct sunshine.

Any inhomogeneity formed or viscosity build up during transport or storage can be reversed using light stirring prior to use and has no influence on product performance.

### SHELF LIFE

Standard shelf life is 180 days from the date of manufacturing, but may be extended based upon retesting by allnex Quality Control.

### TYPICAL PROPERTIES

<b>Density:</b> DIN 53217	1.00 kg/dm <sup>3</sup>
<b>Flash point (estimated):</b> ISO 1523	38 °C

### REMARKS

STM: allnex method of determination (available on request).

STM 001G: spreading agent is xylene. Use a paper clip to spread out.

STM 012E: viscosity measured at 23 °C.