

an acrylic polyol with 2.0% OH (calculated on non-volatiles)

SOLVENT COMPOSITION

Xylene / Butyl acetate = 25 / 25

SPECIFICATIONS

Non-Volatiles: ISO 3251, <i>STM 001G</i>	48 - 52 %
Acid value (as such): ISO 3682, <i>STM 303A</i>	2 - 6 mg KOH/g
Viscosity (23°C at 50 s-1): ISO 3219, <i>STM 012J</i>	3.5 - 5.5 Pa.s
Colour APHA (Lico): ISO 6271, <i>STM 008F</i>	Max. 50 APHA
Appearance: <i>STM 017A</i>	Clear, free of extraneous matter

TYPICAL PROPERTIES

Density: DIN 53217	1.01 kg/dm ³
Flash point: ISO 1523	25 °C

REMARKS

STM: Allnex method of determination (available on request)

TECHNICAL FEATURES

Excellent fast-drying, very good through hardening, good stackability and good compatibility with polyisocyanates.

APPLICATION

Two-component polyurethane lacquers and varnishes (also for wood).

STORAGE CONDITIONS

Storage should be under cover, out of direct sunlight and avoiding extreme temperature changes.

Under normal storage conditions (5 - 35°C, away from extremes) sealed, unopened containers of this material would have a shelf life of 24 months from the date of manufacture. If it is stored for longer than 24 months, it is recommended that the product is rechecked for suitability in the intended application.