

## PRELIMINARY PRODUCT INFORMATION

### TYPE

Medium oil, non drying alkyd resin

### FORM OF DELIVERY (f.o.d.)

80 % in butyl acetate (80BAC)

## SPECIAL PRODUCT

### DEVELOPMENT PRODUCT

**This product is serving for trial purposes only. Deviations which might occur during transfer into manufacturing in a commercial scale are possible and do not constitute any material defect.**

## TENTATIVE PRODUCT DATA

### Determined per batch:

#### Dynamic Viscosity DIN EN ISO 3219

dynamic viscosity (25 1/s; 23 °C)	[mPa.s]	3000 - 4000
--------------------------------------	---------	-------------

#### Iodine Colour Number DIN 6162

iodine colour number		<= 3
----------------------	--	------

#### Acid Value DIN EN ISO 2114

acid value (non volatile matter)	[mg KOH/g]	<= 4
-------------------------------------	------------	------

#### Hydroxyl Value DIN 53240

hydroxyl value (solid matter content)	[mg KOH/g]	125 - 155
--	------------	-----------

#### Non-Volatile Matter DIN 55671

non-volatile matter (120 °C; 5 min)	[%]	78 - 82
--	-----	---------

### Not continually determined:

#### Non-Volatile Matter DIN EN ISO 3251

non-volatile matter (1 h; 125 °C; 1 g)	[%]	78 - 82
---	-----	---------

#### Density (Liquids) DIN EN ISO 2811-2

density approx. (20 °C)	[g/cm <sup>3</sup> ]	1,05
-------------------------------	----------------------	------

#### Flash Point DIN EN ISO 1523

flash point approx.	[°C]	35
------------------------	------	----

## SPECIAL PROPERTIES AND USE

Vialkyd SAC 459n/80BAC is a hydroxy functional, non-drying alkyd resin suitable for crosslinking with polyisocyanates and amino resins.

### STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

## REMARK:

Data contained in this publication are based on careful investigations (and are intended for information only). Due to scale up of this product there is not yet sufficient experience concerning serial production. We can therefore not exclude, that based on future knowledge product data and other indicated properties in upcoming Technical Data Sheets will be subject to change. We reserve the right to leave the product name unchanged, even if product data or other indicated properties will vary from the present product info. Regardless of the data contained in this publication any user is obliged to carry out tests under his own responsibility as to the suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products. We apply our General Sales Conditions.