

COMPATIBILITY

% TIRES 2780	90 75 50 25 10
% of other material	10 25 50 75 90
<i>Alkyd resins</i>	
SETAL 4 XX-60	- - - - -
SETAL 201 WS-60	- - - - -
SETAL 142 VV-55	- - - - +
<i>Amino resins</i>	
SETAMINE US-8 BX-50	+ + + + +
SETAMINE US-8 BB-60	+ - - - -
SETAMINE US-11 BX-68	+ + + + +
SETAMINE US-119 BB-65	- - + - -
SETAMINE US-134 BB-57	+ + + + +
SETAMINE US-138 BB-70	+ + + + +
SETAMINE US-231 BX-62	- - - - -

Suitable mixing proportions (calculated on Non-volatiles) are marked +.
Combinations in the proportions marked - are not recommended.

DILUTABILITY

Aliphatics	white spirit	not dilutable
Aromatics	xylene	dilutable
	toluene	dilutable
Esters	ethyl acetate	dilutable
	butyl acetate	dilutable
Ketones	acetone	dilutable
Alcohols	ethanol	not dilutable
	butanol	not dilutable