

## PRELIMINARY PRODUCT INFORMATION

### TYPE

Acrylic modified, oil-free, saturated polyester resin in aqueous emulsion with incorporated catalyst

### FORM OF DELIVERY (f.o.d.)

60% in butanol/methoxy propoxy propanol (60BMPP)  
(containing also approx. 2 % Isopropanol)

## DEVELOPMENT PRODUCT

**This product, serving for trial purposes only. Deviations which might occur during transfer into manufacturing in a commercial scale are possible and do not constitute any material defect.**

### Neutralization agent

5 % N.N-dimethylethanolamine, as salt

## TENTATIVE PRODUCT DATA

### Determined per batch:

#### Dynamic Viscosity DIN EN ISO 3219

dynamic viscosity (25 1/s; 23 °C)	[mPa.s]	8000 - 14000
--------------------------------------	---------	--------------

#### Non-Volatile Matter DIN EN ISO 3251

non-volatile matter (1 h; 125 °C; 1 g)	[%]	58 - 62
---	-----	---------

### Not continually determined:

#### Colour / Appearance VLN 250

colour	pale yellow
appearance	clear

#### Density (Liquids) DIN EN ISO 2811-2

density approx. (20 °C)	[g/cm <sup>3</sup> ]	1,01
-------------------------------	----------------------	------

#### Flash Point DIN EN ISO 1523

flash point approx.	[°C]	39
------------------------	------	----

## SPECIAL PROPERTIES AND USE

Resydrol VAY 5536w is outstanding suited for the production of waterborne high-quality white and coloured one-coat finishes or top coats with good weathering resistance for industrial applications (machines, instruments). For film formation Resydrol VAY 5536w must be crosslinked with amino resins suitable for aqueous systems. Preferred are hexamethoxymethylmelamine grades.

Stoved coatings stand out because of their high film hardness balanced with extraordinary good flexibility, as well as excellent water and solvent resistance. The adhesion to substrates like iron, aluminium, brass, copper and to galvanized surfaces is very good.

Minimum stoving condition: 140 °C for 30 minutes

Excellent paint stability.

Recommended pH-range: 8,0 - 9,0

## STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 365 days.

## REMARK:

Data contained in this publication are based on careful investigations (and are intended for information only). Due to scale up of this product there is not yet sufficient experience concerning serial production. We can therefore not exclude, that based on future knowledge product data and other indicated properties in upcoming Technical Data Sheets will be subject to change. We reserve the right to leave the product name unchanged, even if product data or other indicated properties will vary from the present product info. Regardless of the data contained in this publication any user is obliged to carry out tests under his own responsibility as to the suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products. We apply our General Sales Conditions.