

A saturated polyester resin.

### SOLVENT COMPOSITION

Xylene

### SPECIFICATIONS

<b>Non-Volatiles:</b> ISO 3251, <i>STM 001G</i>	72 - 74 %
<b>Viscosity (23 °C at 100 s<sup>-1</sup>):</b> ISO 3219, <i>STM 012J</i>	2.8 - 4.4 Pa.s
<b>Acid value (as such):</b> ISO 3682, <i>STM 303A</i>	5.9 - 9.2 mg KOH/g
<b>Colour APHA (Lico):</b> ISO 6271, <i>STM 008F</i>	Max. 150 APHA
<b>Appearance:</b> <i>STM 017A</i>	clear, free of extraneous matter

### TYPICAL PROPERTIES

<b>Density:</b> DIN 53217	1.05 kg/dm <sup>3</sup>
<b>Flash point:</b> ISO 1523	29 °C

### REMARKS

STM: allnex method of determination (available on request).

STM 001G: spreading agent is xylene.

### TECHNICAL FEATURES

High solids content at spraying viscosity, good hardness and gloss.

SETAL 1703 XX-75 can be combined with HMMM-resins or methylated and butylated amino resins for stoving temperatures at 120 °C and higher.

### APPLICATION

- Automotive OEM coatings.
- Industrial stoving systems.

### STORAGE CONDITIONS

Keep container tightly closed and dry in a cool, well-ventilated place. Keep away from heat, sparks, flame and other sources of ignition.

### SHELF LIFE

Standard shelf life is 545 days from the date of manufacturing, but may be extended based upon retesting by allnex Quality Control.