

### TYPE

Hydroxy functional acrylic resin; cross-linkable with polyisocyanates for the production of high solids lacquers

### Average hydroxyl content (solid resin)

approx. 4.4 %

### FORM OF DELIVERY (f.o.d.)

70 % in butyl acetate (70BAC)

### PRODUCT DATA

#### Determined per batch:

#### Dynamic Viscosity DIN EN ISO 3219

dynamic viscosity (25 1/s; 23 °C)	[mPa.s]	2000 - 5000
--------------------------------------	---------	-------------

#### Colour Scale (Hazen) DIN EN ISO 6271-1

Hazen colour value		<=100
--------------------	--	-------

#### Hydroxyl Value (cat.) DIN EN ISO 4629

hydroxyl value (solid matter content)	[mg KOH/g]	135 - 155
--	------------	-----------

#### Colour / Appearance VLN 250

colour		colourless
appearance		clear

#### Non-Volatile Matter DIN EN ISO 3251

non-volatile matter (1 h; 125 °C; 2 g; ethyl acetate)	[%]	68 - 72
--	-----	---------

#### Not continually determined:

#### Density (Liquids) DIN EN ISO 2811-2

density approx. (20 °C)	[g/cm³]	1,04
-------------------------------	---------	------

#### Flash Point DIN EN ISO 1523

flash point approx.	[°C]	30
------------------------	------	----

### SPECIAL PROPERTIES AND USE

Macrynal VSM 2800, in combination with aliphatic polyisocyanates, pre-eminently with Desmodur N 3390 (Covestro), produces high quality, very high solids, 2-pack clearcoats and pigmented topcoats for automotive refinish and industrial lacquers.

Owing to its very high reactivity, Macrynal VSM 2800 is also suitable for the formulation of automotive refinish primer-surfacers.

### STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

### DISTINGUISHING FEATURES

Compared to Macrynal SM 565, Macrynal VSM 2800 provides higher reactivity and, therefore, shorter dry-to-touch time and slightly lower paint solids content.

