

General Description

SETAPOLL™ SP385 is a carboxyl functional polyester resin for combination with β -hydroxyalkyl amide at 93:7 ratio. To be used with SETAPOLL™ SP381 for Architectural, standard bake, dry blend matt pair systems. SETAPOLL™ SP385 has very good overbake stability and is suitable for corona application.

Saturated Polyester Resin

Product Specification

	Limits
Appearance	Pale Granules
Acid value (mg KOH/g)	46-52
Brookfield Viscosity @ 200 °C, mPa.s	1000-3000
Color, b value	Max. 15

Other Properties

	Typical value
Glass transition (°C)	Approx. 60

Extrusion & Application Conditions

Application	
Application	60 micrometer film on 0.6 mm aluminium panel
Curing	10 min @ 200 °C peak metal temperature

Shelf Life

Under normal storage conditions ($\leq 30^{\circ}\text{C}$), the shelf life of the resin will be 24 months from date of manufacturing. For product older than 24 months, it is recommended to check the acid value and the viscosity every year.

Safety & Environmental Protection

For more information, please refer to the Material Safety Data Sheet.

February 2021 – Supersedes previous versions