

INTRODUCTION

SETAL 20-1020 is a high quality, high solids saturated polyester resin for use in thermoset coatings with a high order of durability, color, gloss retention, cured hardness and resistance properties.

TYPE

Saturated polyester resin

FORM OF DELIVERY (F.O.D.)

75% non-volatile in ethyl acetate

PRODUCT DATA

Non-volatile, by weight:	75.0 ± 1.0 %
Viscosity @ 77° F:	Z – Z3 Gardner – Holdt
Color:	2 maximum Gardner
Acid value, on n.v.:	12 maximum mg KOH/g
Appearance:	Clean, clear & free from extraneous matter
Density:	9.40 ± 0.10 lbs/gal
Flash point:	24° F Setaflash
Non-volatiles, by vol.:	68.4%
HEW on n.v.:	400

PERFORMANCE HIGHLIGHTS

- High order of hardness, abrasion- and mar resistance
- Excellent flow, appearance and application properties
- Excellent color, gloss retention and exterior durability

SUGGESTED USES

- Industrial topcoats for large or small appliances and metal cabinetry
- Coatings for business machines and metal office furniture

STORAGE

In the original sealed containers, this product is stable for 2 years at temperatures up to 100°F

PRECAUTIONS

Before using SETAL 20-1020, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation. See the SDS for the recommended storage temperature range for SETAL 20-1020.