

Chlorinated Polyester

INTRODUCTION

EBECRYL® 445 is a reactive chlorinated polyester resin diluted 40% with the reactive diluent trimethylolpropane triacrylate (TMPTA). EBECRYL® 445 is not based on bisphenol A raw materials, and is tin-free. EBECRYL® 445 exhibits good lithographic behavior and pigment wetting properties, and fast cure response in ultraviolet light (UV) curable coatings and inks. Cured films of EBECRYL® 445 display good adhesion to metals, and paper.

PERFORMANCE HIGHLIGHTS

EBECRYL® 445 is characterized by:

- Good wet lithographic behavior
- Fast curing
- Low odor

UV/EB cured formulations based on EBECRYL® 445 are characterized by the following performance properties:

- Good adhesion to metals, and paper

The actual properties of UV/EB cured formulations also depend on the selection of the other formulation components, such as reactive diluent(s), additives and photo initiators.

SUGGESTED APPLICATION

UV/EB curable formulations containing EBECRYL® 445 may be applied by lithographic, screen, gravure, direct or reverse roll, and curtain coating methods.

EBECRYL® 445 is recommended for use in:

- Wet lithographic inks and coatings for paper, and metals
- Adhesion promoter for inks and coatings on metals, and paper

SPECIFICATIONS

Acid value, mg KOH/g	max. 10 - 25
Appearance	Clear liquid
Color, Gardner	max. 3
Viscosity, 60°C, mPa.s	1350 - 1650

TYPICAL PROPERTIES

Density, g/cm ³ at 25°C	1.28
Resin, % by weight	60
TMPTA, % by weight	40

VISCOSITY REDUCTION

EBECRYL® 445 can be further diluted with TMPTA⁽¹⁾ or other reactive monomers such as 1,6-hexanediol diacrylate (HDDA)⁽¹⁾, tripropylene glycol diacrylate (TPGDA)⁽¹⁾ or propoxylated glycerol triacrylate (OTA-480)⁽¹⁾. Although viscosity reduction can be achieved with non-reactive solvents, reactive diluents are preferred because they are essentially 100 percent converted during UV/EB exposure to form a part of the coating or ink, thus reducing solvent emissions. The specific reactive diluents used will influence performance properties such as hardness and flexibility.

⁽¹⁾ product of allnex

PRECAUTIONS

Before using EBECRYL® 445, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. This might cause uncontrollable polymerization of the product with the generation of heat. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Procedures that remove or displace oxygen from the material should be avoided. Do not store this material under an oxygen free atmosphere. Dry air is recommended to displace material removed from the container. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation.

See the SDS for the recommended storage temperature range for EBECRYL® 445.