

An acrylic polyol with 2.4% OH (calculated on non-volatiles)

### TECHNICAL FEATURES

In combination with aliphatic poly-isocyanates: good drying, good through hardening, good chemical resistance, good compatibility with poly isocyanates.

### APPLICATION

Industrial lacquers – clearcoat or pigmented paint.

### SOLVENT COMPOSITION

Xylene / Butyl acetate

### SPECIFICATION

**Non-volatile content:** 59 - 61 %

DIN EN ISO 3251

**Acid value (as such):** 4.3 - 7.8 mg KOH/g

ISO 3682, *STM 303A*

**Viscosity ( 23°C at 50 s-1):** 10 - 20 Pa.s

ISO 3219, *STM 012J*

**Colour APHA (Lico):** max. 100 APHA

ISO 6271, *STM 008F*

**Appearance:** clear, free of extraneous matter

**Density:** 0.99 kg/dm<sup>3</sup>

DIN 53217

**Flash point:** 28 °C

DIN EN ISO 13 736

\* STM: Allnex method of determination (available on request)

\*\* spreading agent, xylene

### STORAGE

Storage should be under cover, out of direct sunlight and avoiding extreme temperature changes.

Under normal storage conditions (5 - 35°C, away from extremes) sealed, unopened containers of this material would have a shelf life of 12 months from the date of manufacture. If it is stored for longer than 12 months, it is recommended that the product is rechecked for suitability in the intended application.