

INTRODUCTION

SETAL 21-3464 is a high solids long-oil alkyd resin designed for use in thermoplastic hot melt traffic paints.

TYPE

Long oil alkyd resin

FORM OF DELIVERY (F.O.D.)

100% theoretical non-volatile

PRODUCT DATA

Non-volatile, by weight:	99.5 maximum %
Viscosity, 77° F:	H – J Gardner – Holdt
Acid value, on n.v.:	4 maximum mg KOH/g
Color:	6 maximum Gardner
Appearance:	Clean, clear & free from extraneous matter
Density:	8.10 ± 0.10 lbs/gal
Flash point:	> 200° F Setaflash

PERFORMANCE HIGHLIGHTS

- Plasticizer with air dry potential
- Excellent application properties via low viscosity
- Good flexibility

SUGGESTED USES

- Thermoplastic hot melt traffic paints
- Viscosity reducer for trade sales long alkyd paints

STORAGE

In the original sealed containers, this product is stable for 2 years at temperatures up to 100°F.

PRECAUTIONS

Before using SETAL 21-3464, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation. See the SDS for the recommended storage temperature range for SETAL 21-3464.