

DESCRIPTION

ETERMINO® 9115-60 is n-butylated urea-formaldehyde resin.

PERFORMANCE

- Fast dry, low temperature curing
- Good hardness & adhesion
- Good cost performance balance

SUGGESTED USES

In combination with alkyd resin, ETERMINO® 9115-60 is recommended for wood, and plywood finishes.

SPECIFICATIONS

Percent Solids, %	62 ± 2
Solvent	n-butanol, Xylol
Viscosity, Gardner-Holdt at 25°C	L - O
Acid Value	2.5 - 4.5
Color, Gardner	max. 1

SUGGESTED FORMULATION

(FOR GUIDANCE ONLY)

		wt
ETERMINO® 9115-60		29.2
ETERKYD 3103-X-70		25
Iso-butanol		4.7
Xylol		18.9
	Mixing	
ETERCOAT 602C		5.9