

### General Description

CRYLCOAT® E 04362 is a superdurable hydroxyl functional polyester resin for use with blocked isocyanates or uretdiones. Coatings based on CRYLCOAT® E 04362 exhibit outstanding outdoor resistance.

### Saturated Superdurable Polyester Resin

Preliminary Technical Data Sheet

### Product Specification

	Limits
<b>Appearance</b>	<b>Pale granules</b>
<b>Brookfield Viscosity @ 200 °C, mPa.s</b>	<b>Approx. 3000</b>
<b>Color, b-value</b>	<b>Max. 15</b>
<b>Hydroxyl value (mg KOH/g)</b>	<b>Approx. 220</b>

### Shelf Life

Under normal storage conditions ( $\leq 25^{\circ}\text{C}$ ), the shelf life of the resin will be 24 months from date of manufacturing. For product older than 24 months, it is recommended to check the acid value and the viscosity every year.

### Safety & Environmental Protection

For more information, please refer to the Material Safety Data Sheet.

July 2020 – Supersedes previous versions

### Other Properties

	Typical value
<b>Glass transition (<math>^{\circ}\text{C}</math>)</b>	<b>Approx. 53</b>