

An acrylic polyol with 1.8 % OH (calculated on non-volatiles).

### SOLVENT COMPOSITION

Butyl acetate

### TECHNICAL FEATURES

Extremely fast drying, very good through hardening, good stackability.

### SPECIFICATIONS

|   |                     |
|---|---------------------|
| <b>Non-Volatiles:</b><br>ISO 3251, <i>STM 001G</i>                          | 51 - 53 %           |
| <b>Viscosity (23 °C at 25 s<sup>-1</sup>):</b><br>ISO 3219, <i>STM 012J</i> | at 51% 12 - 24 Pa.s |
| <b>Viscosity (23 °C at 25 s<sup>-1</sup>):</b><br>ISO 3219, <i>STM 012J</i> | at 52% 15 - 30 Pa.s |
| <b>Viscosity (23 °C at 25 s<sup>-1</sup>):</b><br>ISO 3219, <i>STM 012J</i> | at 53% 19 - 38 Pa.s |
| <b>Acid value (as such):</b><br>ISO 3682, <i>STM 303A</i>                   | 8.2 - 11.7 mg KOH/g |
| <b>Colour APHA (Lico):</b><br>ISO 6271, <i>STM 008F</i>                     | Max. 50 APHA        |
| <b>Appearance:</b><br><i>STM 017A</i>                                       | clear and clean     |

### APPLICATION

Two-component lacquers and varnishes for wood.

### STORAGE CONDITIONS

Keep container tightly closed and dry in a cool, well-ventilated place.  
Keep away from heat, sparks, flame and other sources of ignition.

### SHELF LIFE

Standard shelf life is 720 days from the date of manufacturing, but may be extended based upon retesting by allnex Quality Control.

### TYPICAL PROPERTIES

|                                 |                         |
|---------------------------------|-------------------------|
| <b>Density:</b><br>DIN 53217    | 1.04 kg/dm <sup>3</sup> |
| <b>Flash point:</b><br>ISO 1523 | 23 °C                   |

### REMARKS

STM: allnex method of determination (available on request).

STM 001G: spreading agent is methyl ethyl ketone. Use a paper clip to spread out.