

### General Description

BECKOPOX™ E 04649 is an epoxy functional resin designed as hardener for carboxylated polyester resins for use in the production of hybrid powder coatings. Coatings based on carboxylic polyester such as CRYLCOAT® E 04632 for production of matte dry blend powder coatings with gloss level of 20 – 35% produce outstanding smoothness at cure temperature as low as 130°C on MDF.

### Epoxy functional Resin

Preliminary Technical Data Sheet

### Product Specification

	Limits
Appearance	Pale granules
Brookfield Viscosity @ 175 °C, mPa.s	Approx. 175
Color, b-value	Max. 15
Epoxy EEW (g/eq)	Approx. 550

### Shelf Life

Under normal storage conditions ( $\leq 25^{\circ}\text{C}$ ), the shelf life of the resin will be 12 months from date of manufacturing. For product older than 12 months, it is recommended to check the acid value and the viscosity every year.

### Safety & Environmental Protection

For more information, please refer to the Material Safety Data Sheet.

July 2020 – Supersedes previous versions

### Other Properties

	Typical value
Glass transition ( $^{\circ}\text{C}$ )	Approx. 36