

INTRODUCTION

SETALUX 57-7205 is a HAPs-free acetoacetate functional acrylic resin for use in combination with SETALUX 10-1440 in the isocyanate-free “Ketac” primer system. This system provides very fast dry, good sanding, good adhesion to various substrates and superior topcoat hold-out.

TYPE

Acetoacetate functional acrylic resin

FORM OF DELIVERY (F.O.D.)

45% non-volatile in parachlorobenzotrifluoride

PRODUCT DATA

Non-Volatile, by wt:	45.0 ± 1.0 %
Viscosity (77° F):	Z – Z3 Gardner – Holdt
Acid value:	2 maximum mg KOH/g
Color:	100 maximum APHA
Appearance:	Clean. Clear and free from extraneous matter
Density:	10.50 ± 0.10 lbs/gal
Non-volatiles, by vol:	48.2%
Flash Point:	116° F Setafash
Acetoacetate equiv. wt:	1200 on n.v.

PERFORMANCE HIGHLIGHTS

- Extremely fast air drying
- Excellent filling properties and good sagging resistance
- Easy wet and dry sandability after 1 hr air dry, very short flash time between coats
- Extremely good adhesion on different substrates

SUGGESTED USES

- Non-isocyanate Car Refinish and fleet primer applications
- Non-isocyanate primers for plastics
- Non-isocyanate industrial primer systems for metal

STORAGE

In the original sealed containers, this product is stable for 3 years at temperatures up to 100°F.

PRECAUTIONS

Before using SETALUX 57-7205, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation. See the SDS for the recommended storage temperature range for SETALUX 57-7205.