

INTRODUCTION

SETAL 21-2658 is a medium linseed oil alkyd designed for use in air dry or force dry wrinkle finishes. This resin contributes to cured film toughness; the type of drier blend selected will determine the wrinkle pattern and film thickness.

TYPE

Medium linseed oil alkyd

FORM OF DELIVERY (F.O.D.)

80% non-volatile in methyl propyl ketone / n-butyl acetate
Ratio of solvents: 50 / 50 pbw

PRODUCT DATA

Non-volatile, by weight:	80.0 ± 1.0 %
Viscosity, 77° F:	Z1 – Z3 Gardner – Holdt
Acid value, on n.v.:	12 maximum mg KOH/g
Color:	16 maximum Gardner
Density:	8.85 ± 0.10 lbs/gal
Flash point:	46° F Setaflash
Non-volatiles, by vol.:	74.8%
Reduced viscosity:	N – S Gardner – Holdt @ 70% in MPK/BuAc

PERFORMANCE HIGHLIGHTS

- Cured films have good toughness and flexibility
- Resin provides exterior durability and gloss retention

SUGGESTED USES

- Clear or pigmented wrinkle varnishes
- Textured coatings

STORAGE

In the original sealed containers, this product is stable for 2 years at temperatures up to 100°F.

PRECAUTIONS

Before using SETAL 21-2658, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation. See the SDS for the recommended storage temperature range for SETAL 21-2658.