

## General Description

CRYLCOAT® 2462-2 is a carboxyl functional polyester resin for use with 7% TGIC in the production of powder coatings. Formulations based on CRYLCOAT® 2462-2 exhibit good flow, excellent outdoor durability, flexibility and improved boiling water resistance.

(Formerly CRYLCOAT® E 04663)

## Saturated Polyester Resin

### Product Specification

	Limits
Appearance	Pale granules
Brookfield Viscosity @ 200 °C, mPa.s	4500-6000
Color, b-value	Max. 15
Acid value (mg KOH/g)	31-37

### Other Properties

	Typical value
Glass transition (°C)	Approx. 63

### Shelf Life

Under normal storage conditions ( $\leq 30^{\circ}\text{C}$ ), the shelf life of the resin will be 24 months from date of manufacturing. For product older than 24 months, it is recommended to check the acid value and the viscosity every year.

### Safety & Environmental Protection

For more information, please refer to the Material Safety Data Sheet.

July 2020 – Supersedes previous versions