

INTRODUCTION

SETALUX 17-1265 is a fast drying thermoplastic acrylic resin solution supplied in toluene. This resin exhibits exceptional adhesion, drying, and sanding properties and is designed in automotive refinish primers.

TYPE

Thermoplastic acrylic resins solution

FORM OF DELIVERY (F.O.D.)

40% non-volatile in toluene

PRODUCT DATA

Non-Volatile, by wt:	40.0 ± 1.0 %
Viscosity (77° F):	Z4 – Z6 Gardner Holdt
Acid value, on n.v.:	34 – 40 mg KOH/g
Color:	50 maximum APHA
Appearance:	clean, clear and free from extraneous matter
Density:	8.00 ± 0.10 lbs/gal
Flash Point:	46° F Setaf flash
Non-volatile, by vol:	34.0%
Reduced viscosity:	U – Y Gardner – Holdt @ 30% in toluene

PERFORMANCE HIGHLIGHTS

- Excellent adhesion to metal substrates
- Dries rapidly and sands quickly
- Good hold-out and corrosion resistance

SUGGESTED USES

- Fast drying primers for automotive refinish
- Single component primers
- Fast drying durable aerosol coatings

STORAGE

At temperatures up to 100°F storage stability packed in original containers amounts for 3 years.

PRECAUTIONS

Before using SETALUX 17-1265, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation. See the SDS for the recommended storage temperature range for SETALUX 17-1265.