

**PRELIMINARY PRODUCT INFORMATION**

**TYPE**

Aqueous emulsion of an aliphatic urethane-acryl-hybrid, self-crosslinking, solvent and emulsifier free

**FORM OF DELIVERY (f.o.d.)**

36 % in water (36WA)

**DEVELOPMENT PRODUCT**

This product is serving for trial purposes only. Deviations which might occur during transfer into manufacturing in a commercial scale are possible and do not constitute any material defect.

**Neutralization agent**

0.8 % N,N-dimethyl ethanolamine, as salt

**TENTATIVE PRODUCT DATA**

**Determined per batch:**

**Dynamic Viscosity DIN EN ISO 3219**  
dynamic viscosity [mPa.s] 10 - 350  
(100 1/s; 23 °C)

**pH-Value DIN ISO 976**  
pH-value 7,5 - 8,8  
(10 %)

**Non-Volatile Matter DIN 55671**  
non-volatile matter [%] 35 - 37  
(125 °C; 10 min)

**Not continually determined:**

**Colour / Appearance VLN 250**  
colour colourless to yellowish  
appearance opaque

**Non-Volatile Matter DIN EN ISO 3251**  
non-volatile matter [%] 35 - 37  
(1 h; 125 °C; 1 g)

**Density (Liquids) DIN EN ISO 2811-2**  
density [g/cm<sup>3</sup>] 1,04  
approx.  
(20 °C)

**Flash Point (CCCFP) ASTM D 6450**  
flash point [°C] > 95

**SPECIAL PROPERTIES AND USE**

Daotan TW 7065 is a shear stable, solvent-free, self-crosslinking acrylated polyurethane dispersion providing quick drying and good wetting properties. Cured films are clear - transparent with good chemical- and abrasion resistance.

Daotan TW 7065 is providing excellent adhesion to plastics like e. g. ABS, PC, PP (fl.) and PVC. Accordingly Daotan TW 7065 is recommended for waterborne plastic primer. Furthermore Daotan TW 7065 is also suitable for waterborne Basecoats. These exhibit extraordinary bright metallic-effects.

**STORAGE**

At temperatures from 5 °C to 25 °C storage stability packed in original containers amounts to at least 450 days.

It is important to protect Daotan TW 7065 from frost; at low temperatures it has therefore to be stored under frostproof conditions.

Because of the amphiphilic character of Daotan TW 7065 the product tends to foam. Caused by the self-crosslinking moieties of the product, these foams can establish unreemulsifiable films, also in closed containers. It is strongly recommended to filter the product (5 µm filter) prior to use.

## REMARK

**Data contained in this publication are based on careful investigations (and are intended for information only). Due to scale up of this product there is not yet sufficient experience concerning serial production. We can therefore not exclude, that based on future knowledge product data and other indicated properties in upcoming Technical Data Sheets will be subject to change. We reserve the right to leave the product name unchanged, even if product data or other indicated properties will vary from the present product info. Regardless of the data contained in this publication any user is obliged to carry out tests under his own responsibility as to the suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products. We apply our General Sales Conditions.**