

A thixotropic high solids long oil alkyd.

SOLVENT COMPOSITION

D60 solvent and max. 1.5 % xylene

SPECIFICATIONS

Non-Volatiles: ISO 3251, <i>STM 001G</i>	84 - 86 %
Acid value (as such): ISO 3682, <i>STM 303A</i>	5.8 - 11.2 mg KOH/g
Colour GARDNER (Lico): ISO 4630, <i>STM 008E</i>	Max. 10.0 Gardner
Appearance: <i>STM 017A</i>	max. opaque

TYPICAL PROPERTIES

Density: DIN 53217	0.90 kg/dm ³
Flash point: ISO 1523	70 °C

REMARKS

STM: allnex method of determination (available on request).

STM 001G: spreading agent is xylene. Use a paper clip to spread out.

TECHNICAL FEATURES

Almost insensitive to higher temperatures and presence of polar solvents. Very high solids content of the thixotropic resin.

APPLICATION

SETAL 50293 HD-85 YA will be used in high solids paints for professional decorative application with thixotropic behaviour.

STORAGE CONDITIONS

Keep container tightly closed and dry in a cool, well-ventilated place. Keep away from heat, sparks, flame and other sources of ignition.

SHELF LIFE

Standard shelf life is 545 days from the date of manufacturing, but may be extended based upon retesting by allnex Quality Control.