

### INTRODUCTION

SETALUX 17-7202 is an acetoacetate functional acrylic resin that is combined with a ketimine resin (Setalux 10-1440) to form the NISO non-isocyanate “Ketac” system primer. This system provides very fast dry and cure speed at room temperature. This “Ketac” system also provides good sanding, good adhesion to various substrates and good enamel hold out.

### TYPE

Acetoacetate functional acrylic resin

### FORM OF DELIVERY (F.O.D.)

50% non-volatile in xylene

### PRODUCT DATA

Non-Volatile, by wt.:	50 ± 1.0 %
Viscosity (77° F):	Q – T Gardner Holdt
Acid value, solids:	2 maximum mg KOH/g
Color:	200 maximum APHA
Appearance:	Clean, clear and free from extraneous matter
% acetoacetate on n.v.:	1.2%
Density:	8.2 lbs./gal.
Flash Point:	79° F
Non-volatile, by vol:	43.1%
Acetoacetate equiv. weight:	1150 on solids

### PERFORMANCE HIGHLIGHTS

- Excellent fast air dry to sand times
- Extremely good adhesion on different substrates
- Formulates a 4.2 – 4.6 lb/gal VOC system
- Low toxicity properties

### SUGGESTED USES

- Non-isocyanate Car Refinish and fleet primer applications
- Non-isocyanate primers for plastics
- Non-isocyanate industrial primer systems for metal

### STORAGE

In the original sealed containers, this product is stable for 3 years at temperatures up to 100°F.

### PRECAUTIONS

Before using SETALUX 17-7202, see the Safety Data Sheet (SDS) for information on the identified hazards of the material and the recommended personal protective equipment and procedures.

### STORAGE AND HANDLING

Care should be taken not to expose the product to high temperature conditions, direct sunlight, ignition sources, oxidizing agents, alkalis or acids. Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Wash thoroughly after handling. Keep container tightly closed. Use with adequate ventilation. See the SDS for the recommended storage temperature range for SETALUX 17-7202.