

## General Description

CRYLCOAT® 2572-6 is a high reactive tribo applicable carboxyl functional polyester resin for use with 8-9% Araldite® PT 910 and Araldite® PT 912 in low bake (10 min x 160°C) formulations. Coatings based on CRYLCOAT® 2572-6 exhibit good flow, good mechanical properties and excellent outdoor durability.

(Formerly CRYLCOAT® E 04692)

Preliminary Technical Data Sheet

## Saturated Polyester Resin

### Product Specification

|                                      | Limits        |
|--------------------------------------|---------------|
| Appearance                           | Pale granules |
| Brookfield Viscosity @ 200 °C, mPa.s | Approx. 4100  |
| Color, b-value                       | Max. 10       |
| Acid value (mg KOH/g)                | Approx. 34    |

### Shelf Life

Under normal storage conditions ( $\leq 30^{\circ}\text{C}$ ), the shelf life of the resin will be 24 months from date of manufacturing. For product older than 24 months, it is recommended to check the acid value and the viscosity every year.

### Safety & Environmental Protection

For more information, please refer to the Material Safety Data Sheet.

July 2020 – Supersedes previous versions

### Other Properties

|                       | Typical value |
|-----------------------|---------------|
| Glass transition (°C) | Approx. 63    |